

Mould resin P + Hardener EPH 573	Yields hard elastic, polishable surfaces with good edge strength; consumption approx. 0.5–1 kg/m ²	100 : 17	25	24 h at RT	ca. 65 °C	black	1.5
Mould resin P + Hardener EPH 161	Yields hard elastic, polishable surfaces with good edge strength and high heat distorsion temperature; consumption approx. 0.5–1 kg/m ² . Surfaces not resistant to styrene, i.e. not suitable for polyester resins	100 : 17	90	24 h at RT + annealing 10 h at 60 °C	130–140 °C after annealing 10 h at 100 °C	black	4